

# DECORATIVE PANELS (TAFILAM)

Tafisa® Decorative Panels (TFL)			
Properties	Standard References	Standard Values	Tafisa® Decorative Panels
Wear Resistance	NEMA Ld-3 2005	400 Cycles	Solid Colours** 450 cycles* Woodgrains and Abstracts 150 cycles
Appearance	NEMA Ld-3 2005	N/A	No Surface Defects
Scratch Resistance	EN 438 2.14-91	N/A	3,4 N*
Stain Resistance	NEMA Ld-3 2005	1 to 10 : No Effect 11 to 15 : Moderate Effect	1 to 10 : No Effect 11 to 15 : Moderate Effect
Cleanability	NEMA Ld-3 2005	Maximum 20	Maximum 20
Light Resistance	NEMA Ld-3 2005	Slight Effect	Slight Effect
High Temperature Resistance	NEMA Ld-3 2005	Slight Effect	Slight Effect
Radiant Heat Resistance	NEMA Ld-3 2005	No Effect After 60-secondes Exposure	No Effect After 60-secondes Exposure
Boiling Water Resistance	NEMA Ld-3 2005	N/A	N/A
Impact Resistance	NEMA Ld-3 2005	15 inches - 381 mm	15 inches - 381 mm
Flame-Spread Resistance	ASTM E-84	Classe III ou C	Classe III ou C
Warping	CPA Annex D	N/A	2.6 mm / Linear M
*For Crystalite Texture **Solids 760, 761, 762, 763, 764, 766, 767, 768, 150 cycles NEMA: National Electrical Manufacturers Association, ASTM: American Society for Testing and Materials, EN: European Standard			

Panel Dimensions					
Width		Length		Thickness	
49"	1245 mm	97"	2464 mm	3/8" 7/16"	9,53 mm 11,11 mm
61"	1549 mm	97"	2464 mm	11/16" 1 1/4"	17,46 mm 31,75 mm
49"	1245 mm	97"	2464 mm	1 1/8"	28,58 mm
61"	1549 mm	97" 109"	2464 mm 2769 mm	1 1/2"	38,1 mm
49"	1245 mm	97" 109"	2464 mm 2769 mm	1/2" 5/8"	12,70 mm 15,88 mm
61"	1549 mm	97" 109"	2464 mm 2769 mm	3/4" 1"	19,05 mm 25,40 mm

Tafisa Canada Inc.  
4660 rue Villeneuve  
Lac-Mégantic (Québec) G6B 2C3  
Canada  
1 888 882-3472

06/2015



Une société du groupe / A company of the group

