



West Fraser



Premium MDF Specifications 2015

Imperial	3/8" – 1/2"	9/16" – 7/8"	15/16" – 1 1/4"
Density	48 pcf	47 pcf	46 pcf
Internal Bond	110 psi	110 psi	105 psi
Modulus of Rupture	4,500 psi	4,500 psi	4,000 psi
Modulus of Elasticity	450,000 psi	450,000 psi	450,000 psi
Screw Holding Face	325 lbs	325 lbs	315 lbs
Screw Holding Edge	N/A	300 lbs	300 lbs
Thickness Swell	0.055 in.	7 %	4 %
Maximum Linear Expansion & Contraction	0.3 %	0.3 %	0.3 %
Thickness Tolerance	± 0.005 in.	± 0.005 in.	± 0.005 in.

Metric	9mm - 12 mm	14 mm – 22 mm	23 mm – 32 mm
Density	769 kg/m ³	753 kg/m ³	737 kg/m ³
Internal Bond	0.76 N/mm ²	0.76 N/mm ²	0.72 N/mm ²
Modulus of Rupture	31.03 N/mm ²	31.03 N/mm ²	27.6 N/mm ²
Modulus of Elasticity	3,103 N/mm ²	3,103 N/mm ²	3,103 N/mm ²
Screw Holding Face	1,445 N	1,445 N	1,400 N
Screw Holding Edge	N/A	1,334 N	1,334 N
Thickness Swell	1.40 mm	7 %	4 %
Maximum Linear Expansion & Contraction	0.3 %	0.3 %	0.3 %
Thickness Tolerance	± 0.127 mm	± 0.127 mm	± 0.127 mm

Other Characteristics

- Moisture content: Average moisture content of finished panels as shipped is 4 – 6%.
- Surface Burning Characteristics: Testing completed on Ranger Board MDF, show material being Class III or C in accordance with ULC Standard CAN/ULC-S102.
- Formaldehyde emissions: Ranger Board MDF – Certified CARB Phase 2 compliant (CCR 93120 CARB Composite Wood ATCM).
- Ranger Board is certified with:
 - Composite Panel Association Eco-Certified Composite Grademark Program (ECC 4-11) and ANSI A208.2 - 2009
 - Scientific Certification Services (SCS – MS – 01444)
 - Forest Stewardship Council Standard for Chain of Custody Certification (FSC-STD-40-004 v2-0) and the Standard for Company Evaluation of FSC Controlled Wood (FSC-STD-40-005 v2-0)
- Standard finish on all panels is 150 grit.
- Finished sizes available:
 - Width 48" to 73"
 - Length 48" to 205"
 - Other sizes are available upon request.
- All physical property values represent the compiled average of quality assurance testing conducted on Ranger Premium MDF. Ranger Premium MDF complies with ANSI A208.2 – 2009 using the prescribed test methods in ASTM D-1037.
- Ranger Premium MDF is manufactured from 100% Western white softwoods. Appearance is a consistent light sandy color.

Ranger Board, a Division of West Fraser Mills Ltd.
1250 Brownmiller Rd.
Quesnel, B.C. V2J 6P5

General sales phone #: 250-992-9254 General email: mdf@westfraser.com

Proudly Distributed By



- KAPOLEI, OAHU HI
808-682-0845
- SEATTLE, WA
425-251-1213
- SPOKANE, WA
509-921-7702
- PORTLAND, OR
503-570-0211
- DENVER, CO
303-373-5300
- SALT LAKE CITY, UT
801-972-4215
- BOISE, ID
208-323-7711
- SACRAMENTO, CA
916-381-8440
- PHOENIX, AZ
602-278-5000
- DALLAS, TX
817 633-8333
- HOUSTON, TX
832-200-3555
- SAN ANTONIO, TX
210-666-1966
- LELAND, NC
910-383-2578
- MINNEAPOLIS, MN
763-428-3153
- ELKHART, IN
574-295-7600
- MATTOON, IL
217-234-9663
- GRAND RAPIDS, MI
616-784-9800
- SAN FRANCISCO/ BAY AREA, CA
925-455-5858
- LOS ANGELES/SAN DIEGO, CA
951-653-9433

hardwoods-inc.com