

Trupan VESTA ULEF - Supports LEED® Credits

www.arauco-na.com

The products below are available with ultra-low emitting VESTA Technology :

- Trupan Standard ULEF
- Trupan Fire-Rated ULEF
- Trupan Plus ULEF
- Trupan Lite ULEF
- Trupan High Density Fire-Rated ULEF

TRUPAN VESTA ULEF MDF												
		Malvern, AR				Bennettsville, SC			Sault Ste. Marie, ON			
		Trupan ULEF				Trupan ULEF			Trupan ULEF			
Thickness Range	(in./mm)	3/8" - 1/2"	15mm - 11/16"	18mm - 28mm	1 1/8" - 1 1/2"	3/8" - 13/16"	7/8" - 1 1/8"	1 3/16" - 1 1/2"	4.8mm - 8mm	9mm - 1/2"	9/16" - 7/8"	1" - 1 1/2"
Average MOR	(psi)	3,500	3,500	3,500	3,500	4,000	4,000	4,000	4,200	3,100	3,100	3,800
Average MOE	(psi)	350,000	350,000	350,000	350,000	500,000	500,000	500,000	450,000	400,000	420,000	480,000
Average Internal Bond	(psi)	105	100	95	90	100	90	85	175	120	110	110
Face Screw Hold	(lb)	300	275	275	275	250	250	275	N/A	300	250	275
Edge Screw Hold	(lb)	N/A	225	225	225	225	175	225	N/A	N/A	245	250
Thickness Tolerance	(in.)	+/- .005	+/- .005	+/- .005	+/- .005	+/- .005	+/- .005	+/- .005	+/- .005	+/- .005	+/- .005	+/- .005
Length and Width	(in.)	+/- 1/16	+/- 1/16	+/- 1/16	+/- 1/16	+/- 1/16	+/- 1/16	+/- 1/16	+/- 1/16	+/- 1/16	+/- 1/16	+/- 1/16
Squareness	(in.)	+/- 1/8	+/- 1/8	+/- 1/8	+/- 1/8	+/- 1/8	+/- 1/8	+/- 1/8	+/- 1/8	+/- 1/8	+/- 1/8	+/- 1/8

		Sault Ste. Marie, ON			Sault Ste. Marie, ON		Eugene, OR		Bennettsville, SC
		Trupan Plus VESTA ULEF			Trupan Lite VESTA ULEF		Trupan FR VESTA ULEF		Trupan HD FR VESTA ULEF
Thickness Range	(in./mm)	9mm - 1/2"	9/16" - 7/8"	1" - 1 1/4"	7/16" - 1/2"	9/16" - 1 1/4"	3/8" - 1/2"	5/8" - 3/4"	3/8"
Average MOR	(psi)	3,800	3,800	3,800	2,900	3,200	3,000	3,000	5,000
Average MOE	(psi)	460,000	480,000	495,000	370,000	400,000	300,000	300,000	550,000
Average Internal Bond	(psi)	155	155	145	110	100	85	85	250
Face Screw Hold	(lb)	340	320	320	250	240	280	280	300
Edge Screw Hold	(lb)	N/A	300	300	N/A	210	N/A	230	225
Thickness Tolerance	(in.)	+/- .005	+/- .005	+/- .005	+/- .005	+/- .005	+/- .005	+/- .005	+/- .005
Length and Width	(in.)	+/- 1/16	+/- 1/16	+/- 1/16	+/- 1/16	+/- 1/16	+/- 1/16	+/- 1/16	+/- 1/16
Squareness	(in.)	+/- 1/8	+/- 1/8	+/- 1/8	+/- 1/8	+/- 1/8	+/- 1/8	+/- 1/8	+/- 1/8

- Testing for conformance to the above specifications must be done in accordance with procedures described in the American National Standard for Medium Density Fiberboard (ANSI 208.2-2009 section 5.2 Sampling for Acceptance).
- Complies with formaldehyde emission requirements for MDF in CPA-ECC-2011, ANSI 208.2-2009 and CCR 93120.3 (d) (CARB Composite Wood ATCM Phase II).
- All panels are approved for interior, non-structural application.
- Contains 100% Recycled/Recovered wood content.

California Proposition 65 Requirement:

Warning: Drilling, sawing, sanding or machining wood products generates wood dust, a substance known to the State of California to cause cancer. Avoid inhaling wood dust or use a dust mask or other safeguards for personal protection.

Usage Notes:

Some laminates and coatings applied to Trupan FR MDF may change the flame spread rating. Standard available woodworking glues have been successfully used in lamination. Any adhesive should be tested for compatibility with the chemical system in Trupan FR MDF prior to full-scale gluing. Questions should be directed to the glue supplier. Wood veneers and other laminates should be tested for compatibility with Trupan FR MDF prior to use. Some wood veneers, laminates, and other types of products may have reactions to surface coatings and finishes, glues, pressing temperatures, moisture, contaminants, the chemical systems used to manufacture FR MDF products, the failure to use UV inhibitors, or due to other causes. Reactions may include discoloration to veneer or laminate. ARAUCO is not responsible for discoloration or for claims associated with discoloration. Please contact your Sales Representative for more information.

When using Trupan FR MDF in wall systems, an integral vapor barrier must be a properly installed component of the wall in any of the following conditions: the wall has an exterior side and the wall separates spaces conditioned unequally.

Limitations:

Trupan FR MDF should be specified for interior, non-structural use only and is not intended for use in exterior applications or damp conditions.

Storage and Handling

Trupan MDF products should never be stored or used outdoors. The indoor storage area should be clean, dry, well ventilated, and free of dust, dirt or particles that could contaminate the MDF. Store flat on stickers on a level, hard, dry surface. Constant relative humidity and temperature should be maintained. Before use, allow to stabilize to the same conditions as are expected after the panel is installed. Condition 48 to 72 hours prior to lamination. For more information, see Composite Panel Association Technical Bulletin: Storage and Handling of Particleboard and MDF.

Proudly Distributed By



- KAPOLEI, OAHU HI 808-682-0845
- SEATTLE, WA 425-251-1213
- SPOKANE, WA 509-921-7702
- PORTLAND, OR 503-570-0211
- DENVER, CO 303-373-5300
- SALT LAKE CITY, UT 801-972-4215
- BOISE, ID 208-323-7711
- SACRAMENTO, CA 916-381-8440
- PHOENIX, AZ 602-278-5000
- DALLAS, TX 817-633-8333
- HOUSTON, TX 832-200-3555
- SAN ANTONIO, TX 210-666-1966
- LELAND, NC 910-383-2578
- MINNEAPOLIS, MN 763-428-3153
- ELKHART, IN 574-295-7600
- MATTOON, IL 217-234-9663
- GRAND RAPIDS, MI 616-784-9800
- SAN FRANCISCO/ BAY AREA, CA 925-455-5858
- LOS ANGELES/SAN DIEGO, CA 951-653-9433

hardwoods-inc.com